

T120

- MF CoroTap™ K 机用丝锥 直槽
- MF Tarauds machine CoroTap™ K Goujures droites
- MF Maschinen-Gewindebohrer CoroTap™ K Geradegenutet
- MF Macho Máquina CoroTap™ K Canal Reto
- MF Machos de máquina CoroTap™ K Estrias rectas
- MF Machine CoroTap™ K Straight Flute

CoroTap™ 105

K	
K 1	30-46
K 2	20-72
K 3	30-46
K 4	- - -
K 5	26-40

Din EN-GJMW-350-4/ 0.8035 MC-code: K1.1.C.NS 219 HB				Vc [m/min]	N [rpm]	Vf [mm/min]
		MF	TP			
K1	8	1	46	1849	1849.0	
	10	1	46	1479	1479.0	
	12	1.5	46	1233	1849.5	
	14	1.5	43	986	1479.0	

 ↓ 2xD		Vc [m/min]	N [rpm]	Vf [mm/min]
MF	TP			
8	1	38	1512	1512.0
10	1	38	1210	1210.0
12	1.5	38	1008	1512.0
14	1.5	35	806	1209.0

 2.5xD		Vc [m/min]	N [rpm]	Vf [mm/min]
MF	TP			
8	1	33	1293	1293.0
10	1	33	1035	1035.0
12	1.5	33	862	1293.0
14	1.5	30	690	1035.0

EN-GJL-250/ 0.0625/ SS0125 MC-code: K2.1.C.UT 215 HB	 1.5xD			Vc [m/min]	N [rpm]	Vf [mm/min]
		MF	TP			
K2	8	1	73	2920	2920.0	
	10	1	73	2336	2336.0	
	12	1.5	73	1947	2920.5	
	14	1.5	68	1557	2335.5	

	 ↓ 2xD		Vc [m/min]	N [rpm]	Vf [mm/min]
	MF	TP			
K2	8	1	60	2387	2387.0
	10	1	60	1910	1910.0
	12	1.5	60	1592	2388.0
	14	1.5	56	1273	1909.5

		↓ 2.5xD		Vc [m/min]	N [rpm]	Vf [mm/min]
	MF	TP				
K2	8	1		51	2042	2042.0
	10	1		51	1634	1634.0
	12	1.5		51	1361	2041.5
	14	1.5		48	1089	1633.5

EN-GJS-500/ 0.7050/ SS072 7 MC-code: K3.2.C.UT 199 HB	 K3 ↓ 1.5xD	MF	TP	Vc [m/min]	N [rpm]	Vf [mm/min]
		8	1	46	1849	1849.0
		10	1	46	1479	1479.0
		12	1.5	46	1233	1849.5
		14	1.5	43	986	1479.0

		Vc [m/min]	N [rpm]	Vf [mm/min]
MF	TP			
8	1	38	1512	1512.0
10	1	38	1210	1210.0
12	1.5	38	1008	1512.0
14	1.5	35	806	1209.0

		↓ 2.5xD		Vc [m/min]	N [rpm]	Vf [mm/min]
	MF	TP				
K3	8	1		33	1293	1293.0
	10	1		33	1035	1035.0
	12	1.5		33	862	1293.0
	14	1.5		30	690	1035.0

//Norme et Pays/région//Standard & Land/Region//Padrão & País/Região//Estándar y país/región//Standard & Country/Region											
ISO	MC-code	Dormer AMG	Europe DIN EN	Germany W.-nr	UK BS	Sweden EN SS	USA AISI/SAE/ASTM	France AFNOR	Italy UNI	Spain UNE	Japan JIS
K 铸铁/Fonte/Gusseisen/Ferros fundidos/ Fundición/Cast iron	可锻铸铁/ Fonte malléable/Temperguss/Ferros fundidos maleáveis/Fundición maleable/ Malleable cast iron										
	K1.1.C.NS	3.3	EN-GJMB350-10	0.8135	B 340/12	0815	32510	MN 35-10			FCMW330
	K1.1.C.NS	3.3	EN-GJMB450-6	0.8145	P 440/7	0852	40010	Mn 450	GMN 45		FCMW370
	K1.1.C.NS	3.3	EN-GJMB550-4	0.8155	P 510/4	0854	50005	MP 50-5	GMN 55		FCMP490
	K1.1.C.NS	3.3	EN-GJMB650-2	0.8165	P570/3	0856	A220-70003	Mn 650-3	GMN 65		FCMP590
	K1.1.C.NS	3.3	EN-GJMB700-2	0.8170	P690/2	0862	A220-80002	Mn700-2	GMN 70		FCMP690
	灰口铸铁/ Fonte grise/Grauguss/Ferros fundidos cinzentos/Fundición gris/Grey cast iron										
	K2.1.C.UT	3.1	EN-GJL-100	0.6010		0110	No 20 B	Ft 10 D			FC100
	K2.1.C.UT	3.1	EN-GJL-150	0.6015	Grade 150	0115	No 25 B	Ft 15 D	G 15	FG 15	FC150
	K2.1.C.UT	3.1-3.2	EN-GJL-200	0.6020	Grade 220	0120	No 30 B	Ft 20 D	G 20		FC200
	K2.1.C.UT	3.1-3.2	EN-GJL-200	0.6025	Grade 260	0125	No 35 B	Ft 25 D	G 25	FG 25	FC250
	K2.1.C.UT	3.1-3.2	EN-JLZ	0.6040	Grade 400	0140	No 55 B	Ft 40 D			
	K2.2.C.UT	3.1-3.2	EN-GJL-300	0.6030	Grade 300	0130	No 45 B	Ft 30 D	G 30	FG 30	FC300
	K2.2.C.UT	3.1-3.2	EN-GJL-350	0.6035	Grade 350	0135	No 50 B	Ft 35 D	G 35	FG 35	FC350
	K2.3.C.UT	3.3	GGL-NiCr20-2	0.6660	L-NiCuCr202	0523	A436 Type 2	L-NC 202			
	球墨铸铁/ Fonte ductile/Kugelgraphitguss/Ferros fundidos nodulares/ Fundición nodular/Nodular cast iron										
	K3.1.C.UT	3.3	EN-GJS-350-22-LT	0.7033	-	0717-15	-	-			
	K3.1.C.UT	3.3-3.4	EN-GJS-400-15	0.7040	SNG 420/12	0717-02	60-40-18	FCS 400-12	GS 370-17	FGE 38-17	FCD400
	K3.1.C.UT	3.3-3.4	EN-GJS-400-18-LT	0.7043	SNG 370/17	0717-12	-	FGS 370-17			FCD500
	K3.1.C.UT	3.3-3.4	EN-GJS-800-7	0.7050	SNG 500/7	0727	80-55-06	FGS 500-7	GS 500	FGE 50-7	
	K3.2.C.UT	3.3-3.4	EN-GJS-600-3	0.7060	SNG 600/3	0732-03	-	FGS 600-3			FCD600
	K3.3.C.UT	3.3-3.4	EN-GJS-700-2	0.7070	SNG 700/2	0737-01	100-70-03	FGS 700-2	GS 700-2	FGS 70-2	FCD700
	K3.5.C.UT	3.3-3.4	EN-GJSA-XNiCr20-2	0.7660	Grade S6	0776	A43D2	S-NC 202			

//Norme et Pays/région//Standard & Land/Region//Padrão & País/Região//Estándar y país/región//Standard & Country/Region											
ISO	MC-code	Dormer AMG	Europe DIN EN	Germany W.-nr	UK BS	Sweden EN SS	USA AISI/SAE/ASTM	France AFNOR	Italy UNI	Spain UNE	Japan JIS
K 蠕墨铸铁/Fonte à graphite compact/Gusseisen mit Vermiculargraphit/Ferros fundidos vermiculares/ Fundición de grafito compactado/Compacted graphite iron	蠕墨铸铁/Fonte à graphite compact/Gusseisen mit Vermiculargraphit/Ferros fundidos vermiculares/ Fundición de grafito compactado/Compacted graphite iron										
	K4.1.C.UT	-	EN-GJV-300								
	K4.1.C.UT	-	EN-GJV-350								
	K4.2.C.UT	-	EN-GJV-400								
	K4.2.C.UT	-	EN-GJV-450								
	K4.2.C.UT	-	EN-GJV-500								
	等温淬火球墨铸铁/Fonte ductile bainitique ADI/Bainitisches Gusseisen mit Kugelgraphit/ Ferros dúcteis austemperados/Fundición dúctil austemperizada/Austempered ductile iron										
	K5.1.C.NS	-	EN-GJS-800-8				ASTM A897 No. 1				
	K5.1.C.NS	-	EN-GJS-1000-5				ASTM A897 No. 2				
	K5.2.C.NS	-	EN-GJS-1200-2				ASTM A897 No. 3				
	K5.2.C.NS	-	EN-GJS-1400-1				ASTM A897 No. 4				
	K2.1.C.UT	3.2	GG25								
	K3.1.C.UT	3.3	GGG-40								